



GENERAL INFORMATION:

SP5279/89/99 Universal Primer Filler is a high-solid surfacer with easy application.
Can be finished wet-on-wet.



COMPONENTS:

- SP2009: 2K Hardener Fast (Aus only)
- SP2099: 2K Hardener Medium
- SP2199: 2K Hardener Slow
- SP2299: 2K Hardener Very Fast
- SP2098: MS Hardener Fast
- SP2198: MS Hardener Medium
- SP2501: HS Hardener Medium
- SP2511: HS Hardener Fast
- SP3199: Thinner Medium



AUTOMOTIVE SUBSTRATES:

- Suitable primer
- Cured old coatings
- Certain Plastics



MIXING RATIO:

- 4 : 1 Universal Primer Filler : HS Hardeners + max 15% Thinner Medium
- 3 : 1 Universal Primer Filler : 2K/MS Hardener + max 10% Thinner Medium



GUN SET UP:

	Nozzle (mm)	Air pressure (bar/psi)
Gravity feed	1,3-1,8	3,5-4,5 / 44 - 58
Suction feed	1,4-1,8	3,5-4,5 / 44 - 58
Pressure tank		
Airless/ Airmix		
HVLP	1,3-1,8	See info manufacturer
HE	1,3-1,8	See info manufacturer



APPLICATION:

1-3 coat 60-180 micron 2,4-7,2 mil



POT LIFE at 20°C / 68°F:

20-30 min.



FLASH OFF at 20°C / 68°F:

5 - 10 minutes



DRY TIMES at 20°C / 68°F:

Min: 16 hours

DRY TIMES at 60°C / 140°F:

Min: 20-30 minutes



CLEAN UP:

Gun Cleaner

NEXT LAYER:

2K topcoats and basecoats.

Chemical base	2-Component hydroxyl acrylic resins	
Physical properties	Viscosity	20-22 Dincup 4 / 20°C
	Specific gravity (g/l)	1.596
	Flash point closed cup	27,5°C / 81,5°F
	Vol. % solids	51
	Economy	8 m ² /L/60 µm
	Gloss	86,11 ft ² /Gal/ 2,36mil
	Colour	Matt
		Black/White/Grey

STORAGE / SHELF LIFE:

Under normal storage conditions 10°C - 30°C / 50°F - 90°F up to two years (unopened container).



Use suitable respiratory protection (we recommend the use of a fresh air supply respirator).



NOTES:



GENERAL INFORMATION:

SP5279/89/99 Universal Primer Filler is a high-solid surfacer with easy application. Can be finished wet-on-wet.



COMPONENTS:

- SP2099: 2K Hardener Medium
- SP2199: 2K Hardener Slow
- SP2198: MS Hardener Medium
- SP2501: HS Hardener Medium
- SP3199: Thinner Medium



AUTOMOTIVE SUBSTRATES:

- Suitable primer
- Cured old coatings
- Certain Plastics



MIXING RATIO:

- 4 : 1 Universal Primer Filler : HS Hardeners + max 15% Thinner Medium
- 3 : 1 Universal Primer Filler : 2K/MS Hardener + max 10% Thinner Medium



GUN SET UP:

	Nozzle (mm)	Air pressure (bar/psi)
Gravity feed	1,3-1,5	3,0-3,5 / 44 - 58
Suction feed	1,4-1,6	3,0-3,5 / 44 - 58
Pressure tank	-	-
Airless/ Airmix	-	-
HVLP	1,3-1,5	See info manufacturer
HE	1,3-1,5	See info manufacturer



APPLICATION:

- 1 coat



POT LIFE at 20°C / 68°F:

30 min.



FLASH OFF at 20°C / 68°F:

15 - 20 minutes



DRY TIMES at 20°C / 68°F:

Min: 16 hours

DRY TIMES at 60°C / 140°F:

Min: 20 - 30 minutes



CLEAN UP:

Gun Cleaner

NEXT LAYER:

2K topcoats and basecoats.

Chemical base	2-Component hydroxyl acrylic resins	
Physical properties	Viscosity	20-22 Dincup 4 / 20°C
	Specific gravity (g/l)	1.596
	Flash point closed cup	27,5°C / 81,5°F
	Vol. % solids	51
	Economy	8 m ² /L/60 µm
		86,11 ft ² /Gal/ 2,36mil
	Gloss	Matt
	Colour	Black/White/Grey

STORAGE / SHELF LIFE:

Under normal storage conditions 10°C - 30°C / 50°F - 90°F up to two years (unopened container).



Use suitable respiratory protection (we recommend the use of a fresh air supply respirator).



NOTES:

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. © 2012 The Valspar Corporation. All rights reserved.