

## GENERAL INFORMATION

SP5279 Universal Primer Filler Black is a high-solid surfacer with easy application and excellent sanding properties. Can be finished wet-on-wet.

### MIXING RATIO



3 : 1 Universal Primer Filler : 2K/MS Hardener  
+ max 20% Thinner Medium  
4 : 1 Universal Primer Filler : HS Hardener  
+ max 30% Thinner Medium  
6 : 1 Universal Primer Filler : HS420 Hardener  
+ max 35%

### GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,5	See info manufacturer
HE	1,3-1,5	See info manufacturer

### APPLICATION



1 coat 20-25 µm (0,8-1,0 mil)

### FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F		FORCED DRY 60°C / 140°F	
Flash off	15 - 20 minutes	Flash off	15 - 20 minutes	
Dust free	15 - 20 minutes	Dust free	-	
Dry to handle	-	Dry to handle	-	
Dry to tape	-	Dry to tape	-	
Dry to sand	-	Dry to sand	-	
Dry to polish	-	Dry to polish	-	

### SUBSTRATES



SP5279 Universal Primer Filler Black should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition.

**(Use SP5499 Etch Primer for maximum durability and rust protection.)**

### POT LIFE AT 20°C / 68°F



30 minutes

### COMPONENTS



SP2099 2K Hardener Medium  
SP2199 2K Hardener Slow  
SP2198 MS Hardener Medium  
SP2298 MS Hardener Slow  
SP2501 HS Hardener Medium  
SP2521 HS Hardener Slow  
SP2599 HS420 Hard Medium  
SP3199 Thinner Medium  
SP3299 Thinner Slow

### ADDITIVES



-

### SURFACE PREPARATION



Pre clean the surface with SP6499 Silicone Remover wipe on and wipe dry. Sand surface with P180—P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with SP6499 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



**Mask entire vehicle to eliminate unwanted overspray.**

### NEXT LAYER



-

Chemical Base	Polyurethane primer based on combination of hydroxy acrylate resins.	
Physical Properties	Viscosity	20-22 Dincup 4 / 20°C
	Specific gravity (kg/l)	1,34
	Flash point closed cup	27,5°C / 81,5°F
	Volume % Solids	37,8
	Economy	15 m <sup>2</sup> /L/25 µm 616 ft <sup>2</sup> /Gal/ 1mil
	Gloss	Matt
	Colour	Black



# SP5279

Universal Primer Filler Black

## PROTECTION



Use suitable respiratory protection (we recommend the use of a fresh air supply respirator).

## CLEAN UP



Gun Cleaner

## STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



## NOTES